

[First Hit](#) [Fwd Refs](#)[Previous Doc](#)[Next Doc](#)[Go to Doc#](#)

Generate Collection

Print

L1: Entry 17 of 19

File: USPT

Nov 14, 1978

DOCUMENT-IDENTIFIER: US 4125503 A

TITLE: Ultraviolet curing emulsion systems

Detailed Description Text (2):

50 parts of an epoxy diacrylate made by reacting hydroxy ethyl acrylate with a diglycidyl ether of bisphenol A having a molecular weight of about 390 is dissolved in 50 parts of butyl carbamoyl ethyl acrylate, and the solution is mixed with 5 parts of benzophenone photosensitizer and 10 parts of Pluronic F 127 emulsifier. This mixture is subjected to high speed agitation and 100 parts of deionized water is added slowly to produce an emulsion having an average particle size of less than about 1 micron.

[Previous Doc](#)[Next Doc](#)[Go to Doc#](#)

Refine Search

Search Results -

Terms	Documents
photosensitizer same (pluronic or poloxamer)	19

Database:

US Pre-Grant Publication Full-Text Database
US Patents Full-Text Database
US OCR Full-Text Database
EPO Abstracts Database
JPO Abstracts Database
Derwent World Patents Index
IBM Technical Disclosure Bulletins

Search:

Search History

DATE: Friday, May 18, 2007 [Purge Queries](#) [Printable Copy](#) [Create Case](#)

Set Name **Query**
side by side

Hit Count **Set Name**
result set

DB=PGPB,USPT,USOC,EPAB,JPAB,DWPI,TDBD; PLUR=YES; OP=OR

L1 photosensitizer same (pluronic or poloxamer)

19 L1

END OF SEARCH HISTORY